

Composite Cloth Topmesh 3-layer - Technical Data

Designation		Geometrical pore size µm	Thickness mm	Porosity %	Pressure drop mbar	A _s mm ² /cm	R _p N/cm	Weight kg/m ²	Eu
Topmesh 3-layer	TM3-KT 2	10	2,0	60	3,54	3,6	573	6,60	2.682
	TM3-KT 5	14	2,0	60	2,77	3,6	573	6,60	2.099
	TM3-KT 10	21	2,0	60	1,72	3,6	573	6,60	1.298
	TM3-BM 15	15	2,0	60	0,62	3,6	573	6,60	469
	TM3-BM 20	20	2,0	60	0,58	3,6	573	6,20	439
	TM3-BM 25	25	2,0	60	0,47	3,6	573	6,20	356
	TM3-BM 30	30	2,0	60	0,35	3,6	573	6,20	265
	TM3-QM 40	42	2,0	60	0,13	3,6	573	6,10	98
	TM3-QM 50	50	2,0	60	0,11	3,6	573	6,10	83
	TM3-QM 60	63	2,0	60	0,08	3,6	573	6,10	61
	TM3-QM 80	80	2,0	60	0,07	3,6	573	6,10	53
	TM3-QM 100	100	2,0	60	0,07	3,6	573	6,20	53
	TM3-QM 150	160	2,0	60	0,06	3,6	573	6,20	45
	TM3-QM 200	200	2,0	60	0,06	3,6	573	6,20	45
	TM3-QM 500	530	2,0	60	0,03	3,6	573	6,20	23

The pressure drop has been calculated for gas at an approach velocity of approximately 20m/min. These values may be used to compare composite cloths.

As: the effective cross section at the cutting edges, which run parallel to the wires to absorb drag.

R_p: is the yield strength value for the load on the composite cloth perpendicular to cross section As, which must not be exceeded.

Eu: The non-dimensional Euler number describes the ratio of pressure forces to inertial forces for the different weave specifications at similar flow conditions. The higher the Euler number of a weave specification, the higher the pressure loss of this weave specification will be. The Euler number allows comparison of differing weave specifications in terms of pressure loss.

The geometric pore size defines the diameter of the largest sphere passing through the weave.

The values given in this table are typical values for the composite cloths. They should not be used to infer any warranted qualities. We reserve the right to make technical changes and enhancements at any time.